

BACKING ROD DATA SHEET

POLYETHYLENE FOAM ROD

Typical Physical Properties

Colour:	Black or White	
Density	37 kgm ³	
Water Absorption	Less than 1	
Thermal Conductivity (kcal/m.h.grd)	@0°C	0.030
	@20°C	0.031
Heat Shrinkage	After 24hrs @70°C	Less than 1%
	After 24hrs @ 90°C	Approx 1%

Water Resistance: (Subject to 400 hours of UV irradiation in Weatherometer)

Exposure (hours)	Tensile Strength (kg/cm ²)	Elongation (%)
0	3.0	26.3
24	3.3	35.0
72	3.7	46.9
168	3.6	39.8
400	2.7	20.0

Application Guide

Foam Sealant Pty Ltd recommends pre-testing all sealants under individual application conditions and materials used prior to commercial use.

Typical Applications

Vertical and horizontal joint filler in concrete and between pre-cast concrete panels, interior walls, sealing skylights, draught proofing, dust sealing and truck and trailer construction.

Disclaimer All figures shown above represent typical test results in laboratory conditions, and are given without guarantee since the conditions of use are beyond the control of our company. Width and thickness tolerances +/- 20%. It is the customer's responsibility to satisfy themselves that the product is fit for the purpose for which they intend to use it and that the actual conditions of use are suitable.



Polyethylene Foam Rod for Expansion Joints and Space Fillers.

Excellent dimensional stability allows it to withstand years of compression and expansion

Low moisture absorption (Less than 1%)

High resistance to weathering, ageing, ultra violet light and most chemicals

Limited Warranty

For a period of six months from the date of first sale, FOAM Sealant Pty Ltd warrants this product to be free from defects in materials and workmanship. Our only obligation will be to replace any portion proving to be defective, or at our option, to refund the purchase price thereof.

The user assumes all other risk if any, including the risk of injury, loss or damage, direct or consequential arising out the use, misuse or inability to use this product. This warranty is in lieu of the warranties of merchantability, fitness for particular purpose and all other warranties expressed or implied. No deviation is authorised.

FOAM Sealant Pty Ltd

ACN 068 983 755 ABN 83 197 550 989

48-52 Micro Circuit Dandenong South 3175 Victoria
Telephone (03) 9702 9989 Facsimile (03) 9799 6304
Email sales@foamsealant.com.au