

# V730 SERIES

Soft, Closed-Cell, Polyvinyl Chloride Foam



**FOAM** Sealant

ISO 9001:2015 CERTIFIED

**Norseal® V730** series is a closed-cell, low density PVC sealant foam with pressure-sensitive adhesive on one side.

The **Norseal V730** series is specially designed to provide the following features:

- Rolls are dimensionally stable — will not ooze, drip or run under compression
- Controls sound transmission and vibration — ideal for acoustical partitions
- Low thermal conductivity improves the energy efficiency of your structure
- Excellent light, dust and moisture seal and for all general sealing needs
- Closed cell content develops positive seal at only 30% compression
- Low deflection force reduces distortion of adjacent material
- Easy to radius, enhancing positive seal on curved surfaces

## Available Sizes

Standard thickness: .125, .188, .25, .375, .50, .625 and .75 in. (3.2, 4.8, 6.4, 9.6, 12.7, 15.9 and 19 mm)

Master roll size: 56 in. (1422 mm) width. Length varies with thickness.

Special thickness and roll sizes also available.



## Applications

- Vending machines
- Hot tubs
- Cold storage room
- Acoustical partitions
- Culvert pipes
- Suspended ceilings
- Seals for flashing
- Saunas
- Computer cabinet dust and noise seal
- Rooftop air conditioner insulation
- Dust seal on analytical equipment



**FOAM Sealant Pty Ltd**

SYDNEY | MELBOURNE | BRISBANE | PERTH

E sales@foamsealant.com.au | P 1300 000 205 | W foamsealant.com.au

ACN 068 983 755 ABN 83 197 550 989 Copyright © Foam Sealant 2021

**SAINT-GOBAIN**

**NORSEAL**

## Norseal V730 – Properties

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

Property	Test Method	Value or Rating
Density: lbs./cu. ft. (kg/m <sup>3</sup> )	ASTM D1667	6 (96.1)
Hardness: Shore 00	ASTM D2240	13
Force to Compress: psi (kPa)*	ASTM D1667	2.0 (13.8)
Compression Deflection: psi (kPa)*	ASTM D1667	1.1 (7.6)
Compression Set: % lost fr. orig. ht.*	NTP-37	7
Water Absorption (% by volume)*	NTP-35	4
90° Peel Adhesion: oz./in (N/m) 15 min. dwell	PSTC-2	16 (175)
Elongation %	ASTM D412 Die A	140
Tensile: psi (kPa)	ASTM D412 Die A	15 (130)
Thermal Conductivity: BTU, in./hr.ft. <sup>2</sup> °F	ASTM C518	25
Colour	-	Grey

\* Based on 30% compression  
NTP: Internal Test Procedure

## Options (subject to minimum order requirements)

Adhesive base: No adhesive, available upon request.

Liner: Permanent PET film available upon request.

## Important Instructions

Because we cannot anticipate or control every potential application, we strongly recommend testing of this product under individual application conditions prior to commercial use. The product contains plasticiser, which may adversely affect some plastics.

Surfaces must be clean and free of oil, grease, moisture, dust and dirt. Isopropyl alcohol is good for cleaning the surface. Do not remove liner until tape is in proper position. Avoid touching adhesive surface before application. The adhesive is intended for positioning during the assembly process. The foam tape is secured in the joint by compression of the adjacent substrates.

The application temperature should be between 40°F and 125°F (4°C to 52°C). It is not recommended to apply these sealants at temperatures below 40°F (16°C), as the adhesive does not flow in this condition and can result in poor bonding. Recommended service temperature is between -15°F to 160°F (-26°C to 71°C).

## Shelf Life

6 months after the date of sale when stored in original packaging at temperatures up to 70°F (21°C) and 50% relative humidity.

## Norseal V730 – Standard Roll Sizes

Product No.	Thickness in. (mm)	Length ft.(m)
V734	.125 (3.2)	100 (30.5)
V736	.188 (4.8)	50 (15.3)
V738	.25 (6.3)	50 (15.3)
V7312	.375 (9.5)	25 (7.6)
V7316	.5 (12.7)	25 (7.6)
V7320	.625 (15.9)	20 (6.1)
V7324	.75 (19.1)	15 (4.6)

3" I.D. cardboard cores standard



**IMPORTANT:** It is the user's responsibility to ensure the suitability and safety of Saint-Gobain products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

**WARRANTY:** For a period of 24 months, Saint-Gobain warrants this product(s) to be free from defects in manufacturing. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

For more information see: [www.tapesolutions.saint-gobain.com](http://www.tapesolutions.saint-gobain.com)